



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

HB/B
6/6/03
RECEIVED
JUN 03 2003
TC 1700

In re Application of : PATENT APPLICATION
CLETUS N. WELCH et al. :
Serial No. 09/755,147 : Group Art Unit: 1711
Filed: January 8, 2001 : Examiner: MELANIE D. BISSETT
For: PHOTOCROMIC POLYURETHANE :
COATING AND ARTICLES HAVING :
SUCH A COATING :
Docket No: 1582A1/RCE

REPLY FILED IN CONJUNCTION WITH RCE UNDER 37 CFR 1.114

Hon. Commissioner of Patents and Trademarks
Washington, D.C. 20231

Sir:

This reply is being filed in conjunction with a Request for Continued Prosecution under 37 CFR 1.114. The following amendment and remarks are respectfully submitted for consideration by the Examiner in charge of the above-captioned application.

I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to:

Hon. Commissioner of Patents and Trademarks
Washington, DC 20231

5/27/03

(Date)

Norma J. Golling
(Signature)
Norma J. Golling

Typed or printed name of person signing certificate

RECEIVED

MAY 27 2003

OFFICE OF PETITIONS

RECEIVED

MAY 28 2003

OFFICE OF PETITIONS

AMENDMENTS

In the application for which continued examination has been requested, Claim 1 has been amended as follows:

1. (Amended) An article comprising, in combination, a substrate, and a photochromic polyurethane coating on at least one surface of said substrate, said coating having a Fischer microhardness of from 50 to 150 Newtons per mm^2 , wherein the improvement comprises preparing said photochromic polyurethane coating from components comprising:

(a) polycarbonate polyol(s) comprising less than 10 mole percent of cycloaliphatic diol, said polycarbonate polyol having a molecular weight of from 500 to 5,000 grams per mole;

(b) optionally, a different organic polyol having a molecular weight of at least 500 grams per mole;

(c) an isocyanate;

(d) photochromic compound(s); and

(e) optional catalyst;

said components being used in such proportions to produce a photochromic polyurethane coating exhibiting less than 25% swell in the Percent Swelling Test.